



Gauge	Weight (lbs. ft)	Area (in ²)	I _x (in ⁴)	r _x (in ⁴)	I _y (in ⁴)	r _y (in ⁴)
20	0.681	0.200	0.071	0.596	0.071	0.596
18	0.877	0.258	0.090	0.592	0.090	0.592
16	1.227	0.361	0.123	0.583	0.123	0.583
14	1.560	0.460	0.152	0.575	0.152	0.575

Technical Data:

Truss components are manufactured from steel conforming to ASTM A-653 or ASTM A-500 and have galvanized coatings in accordance with ASTM A-924 and ASTM A-653, G-90 minimum or G-90 equivalent exterior coating weight (G-60 on CW20). Structural properties of Dynatruss chord and web members are calculated in accordance with the AISI (American Iron and Steel Institute) "Specification for the Design of Cold-Formed Steel Structural Members, August 1986 Edition with December 11, 1989 Addendum." Dynatruss also conforms to AISI Standard for Cold-Formed Steel Framing-Truss Design, December 2004 Edition.